



# MAXPROTECT MATT-PAINT PROTECTION FILM

## MAXPROTECT MATT Technical Data Sheet

MAXPROTECT MATT offers breakthrough technology for paint protection applications utilising an advanced, self-healing, solvent resistant top-coat formulation allowing for easy installation as well as increased longevity. The product is available in 1.52m widths. Outdoor Durability is 7 years.

### 1. Product Construction.

|              |
|--------------|
| Hard Coating |
| TPU film     |
| PSA          |
| PET Liner    |

### 2. Appearance Performance. (Visual Inspection)

|                       |           |                     |
|-----------------------|-----------|---------------------|
| Film Fitting Bubble   |           | Visual Invisibility |
| Film Fitting Stain    |           | Visual Invisibility |
| Crystal & Bump point  | 0.1-0.6mm | Uncountable         |
|                       | 0.7-2.9mm | Maximum 20          |
|                       | ≥3.0mm    | Allow 1             |
| Cotting Mat           |           | Visual Invisibility |
| Adhesive Surface Line |           | Visual Invisibility |

### 3. Physical Performance (Lab Test)

| Items                                      | MAXPROTECT PPF MATT       | Test        |
|--|---------------------------|-------------|
| Gloss Rate (60°)                           | 10~15 (%)                 | GB 8807     |
| Weight (Glue)                              | 25~30 (g/m <sup>2</sup> ) | GB/T 4669   |
| Thickness (Silicon Protection Film)        | 45~55 (um)                |             |
| Thickness (TPU&HC&Adhesive)                | 165~195 (um)              | GB/T 7125   |
| Thickness (PET Liner)                      | 70~80 (um)                |             |
| Elongation Rate at Break (Hard Coating/MD) | 90~120 (%)                | GB/T 1040.1 |
| Dimensional Stability (MD)                 | ≤0.5 (mm)                 | FTM 14      |
| Dimensional Stability (CD)                 | ≤0.4 (mm)                 |             |
| Peel Adhesion                              | ≤0.35 (N/25mm)            | GB/T 2792   |
| Initial Adhesive                           | ≥8 (N/25mm)               | FTM 9       |
| 24h, 180°Peel                              | ≥15 (N/25mm)              | GB/T 2792   |

#### \*Testing Method Direction:

- The elongation at break of the HC protective film shall be as specified in GB/T 1040.1 Determination of Tensile Properties of Plastics, Part 1 General, and the elongation at break of the finished product when the HC coating is broken during the tensile testing
- Storage of aging peeling force means that the sample is cured at 65 ° C for 72 hours, and the peeling force test is carried out according to GB/T 2792;
- Application of aging peeling force means that the sample is cured after being cured at 65 ° C for 72 hours, and then cooled to a natural temperature for 180 ° peeling force testing.

### 4. Characteristic.

|                            |                            |                                   |
|----------------------------|----------------------------|-----------------------------------|
| Scratch Repairment         | Heat repairable            | (0.1mm) Copper brush & drying gun |
| Water Contact Angle        | ≥95°                       | DL/T864                           |
| Acid and Alkali Resistance | No visible visible coating | Experimental Method               |
| Yellowing Resistance       | ≤2                         | QUV Method                        |
| Anti-stain                 | No visible visible stain   | Rainyl Method                     |

#### \*Testing Method Direction:

- About Scratch Repairment, use copper wire brush with a thickness of 0.1mm or less. After the coating surface is brushed 10 times in a circle, after heating with a baking gun or 100
- About Acid and Alkali Resistance, 10% solubility hydrochloric acid, 0.1mol/L sodium hydroxide solution, after being applied to the surface of the sample for 24h, the appearance of the sample is free of visible visible bubbles, cracks and other coating defects
- About Anti-stain, use the equipment with UV radiation, heating and spraying to destroy the sample. The parameter setting refers to the corresponding regulations of GB/T 16422.2.

### 5.Storage Condition.

|             |            |
|-------------|------------|
| Temperature | 15~25 (°C) |
| Humidity    | 40~60 (%)  |

Remarks: MAXPROTECT PPF need to be stored in their original packing and with the original protection materials.. In order to avoid loss of quality, After the package is removed, the remaining parts must be removed the silica protective film in time, or else it is possible to cause arching and fogging during the surface.

### 6.Application Condition.

|                  |                        |
|------------------|------------------------|
| Temperature      | 15~25 (°C)             |
| Humidity         | 40~80 (%)              |
| Cleanness degree | Clean, no visible dust |

#### Remarks:

- All MAXPROTECT PPF paint protection film products shall be cut and engraved in the corresponding environment during the use process to avoid the influence of temperature and static electricity on the product appearance and performance.
- Before the construction, the cleaning and pretreatment of the automobile paint surface must be done strictly to avoid the abnormal quality of the last issue caused by the residual particles and oil stains on the paint surface;
- Within one week of construction, the car washing shall be avoided to avoid the continuous drenching of rain water, ensure that the adhesive and paint surface are fully wetted, and give full play to the best adhesion effect.

### 7.warranty Conditions.

|                    |  |
|--------------------|--|
| Durability Periods | Z F B S T  |
| Warranty contents  | Cracking of base material, peeling off of coating and bubbling of rubber layer |

#### \*Remarks

- All MAXPROTECT PPF paint protection film products shall meet the specified storage conditions and the requirements of standard construction procedures;
- All items within the warranty scope of PPF paint protective film products must strictly comply with the product use and maintenance specifications. For details, please refer to the identification card and corresponding official statement provided with the goods in the product package.

